

CHERAN SPINNER PRIVATE LIMITED
TEST RFEPORT

DATE: 30.06.2021

1	COUNT	Ne 30/1(SLUB)
2	MATERIAL & BLEND	VISCOSE-100%
4	ACTUAL COUNT Ne	30.5
5	C.S.P	2500
6	COUNT CV	1.5
7	STRENGTH CV	1.5
8	T.P.I / T.P.M	19.59/771
9	R.K.M * (TENSOMAXX)	16.5
10	R.K.M CV	7.5
11	ELONGATION	9.5
12	ELONGATION CV	6.5
13	SLUB LENGTH	MIN-(1.47) TO MAX-(2.36)
14	SLUB DIA	1.95
15	SLUB PER METRE	3.35

AUTOCONED / SPLICED

** HAIRINESS (H) Tested in UT 4 SE.

