

Style TEST Sample ID 07955 Nom. count Nm 28.5 Norm. twist 0 T/m
 Tests 10 / 1 v= 400 m/min t= 1 min Meas. slot 3 Short staple

Standard Table CS OH

Article YARN Material class Yarn Mach. Nr. 29
 Uster Statistics
 Fiber Cotton 0% Cotton 0% Cotton 0%
 COUNT; 30s. S. SILVER

Total tests : 10 / 10 Single test(s)

Nr	U%	CVm	Thin -30%	Thin -40%	Thin -50%	Thick +35%	Thick +50%	Thick +70%	Neps +140%	Neps +200%	Neps +280%
	%	%	/km	/km	/km	/km	/km	/km	/km	/km	/km
	12.95	16.34	3558	530.0	30.0	572.5	52.5	0.0	4105	670.0	50.0
	12.64	16.01	4060	667.5	60.0	587.5	52.5	0.0	5760	1005.0	102.5
	12.47	15.74	3310	405.0	20.0	532.5	42.5	0.0	4355	610.0	52.5
	11.82	14.95	2633	230.0	2.5	395.0	40.0	0.0	3633	470.0	30.0
	13.17	16.67	3490	492.5	20.0	587.5	80.0	2.5	4223	722.5	110.0
	12.19	15.35	3140	315.0	10.0	567.5	55.0	5.0	4360	807.5	90.0
	12.35	15.60	3740	477.5	20.0	537.5	42.5	0.0	3980	580.0	55.0
	12.73	16.14	3635	447.5	17.5	622.5	60.0	5.0	5190	830.0	97.5
	12.29	15.85	3488	450.0	25.0	587.5	40.0	0.0	5085	935.0	112.5
	13.11	16.55	4453	640.0	25.0	627.5	75.0	5.0	5363	1007.5	112.5
Mean	12.57	15.92	3551	465.5	23.0	561.8	54.0	1.8	4605	763.8	81.3
CV	3.4	3.4	13.9	28.5	66.0	11.8	26.3	135.5	15.1	24.2	38.2
s	0.43	0.54	494	132.8	15.2	66.2	14.2	2.4	694	184.8	31.1
Q95	0.31	0.38	353	95.0	10.9	47.3	10.2	1.7	496	132.2	22.2
Max	13.17	16.67	4453	667.5	60.0	627.5	80.0	5.0	5760	1008	112.5
Min	11.82	14.95	2633	230.0	2.5	395.0	40.0	0.0	3633	470.0	30.0

U % = 12.57

THIN (-50%) = 23.0

THICK (+50%) = 54.0

NEPS (280%) = 81.3

TOTAL 158.3

N.C. 