

Palani YK, Dindigul - 624 615

SpinSoft **MAG**
Version 5.0.8 beyond quality

Test Report - CSP

Version 4.0.6 beyond quality

Dry : 77°F		Wet : 69°F		RH : 66.00 %		Test Date & Time : 12-Jul-24		3:36 pm	
D	Test ID : 15,349	No. of Test : 8	Count Type : 61 pc	Hom. Strength : 50 (lbf)					
T	Dept. : Ring Frame	Lot No. :	Hom. Count : 61.5 (HeC)	Sam. Length : 120.00 yard					
D	Shift : General	Operator : operator							
M	M/c No. : R/F13	Test No.	Weight (grams)	Count (HeC)	RH Count (HeC)	Strength (lbf)	CSP	RH CSP	Elongation (%)
		1	1.093	59.275	59.358	49.38	2927	2930	6.59
		2	1.049	61.762	61.848	49.50	3057	3060	7.14
		3	1.051	61.644	61.730	51.30	3162	3166	6.79
		4	1.078	60.100	60.184	54.75	3290	3294	6.88
		5	1.092	59.330	59.413	51.64	3064	3067	7.08
		6	1.054	61.469	61.555	48.81	3000	3003	6.64
		7	1.028	63.023	63.111	52.95	3337	3340	7.11
		8	1.059	61.179	61.264	47.38	2899	2902	6.79
		Average	1.063	60.973	61.058	50.71	3092	3095	6.88
		CV %		2.14	2.14	4.74	5.17	5.18	3.10
		Min.		59.275	59.358	47.38	2899	2902	6.59
		Max.		63.023	63.112	54.75	3337	3340	7.14
		Range		3.748	3.753	7.37	438	438	0.55
		SD		1.30	1.31	2.40	159.94	160.18	0.21
		Q95 (±)		1.06	1.06	1.96	130.40	130.60	0.17
		Q99 (±)		1.55	1.55	2.85	189.72	190.01	0.25

107
33

RPM Value : 20.586 RH RPM Value 20.608

Remarks :

OPERATOR

QC INCHARGE

VP